



MaxiFlax

Crack Bridging Coating

Product description:

Flexible acrylic coating for bridging gaps; versatile, produced in four different textures: Smooth (orange peel); Fine (0.3 mm); Medium (1mm) and Coarse (1.5 mm).

Uses:

MaxiFlax is suitable for bridging gaps up to 2 mm wide.

Properties:

- Bridging gaps of up to 2 mm.
- Flexible, impermeable to water and breathable.
- Easy to work with; excellent adhesion.
- High UV resistance.
- Non-toxic.

Application instructions:

- The application surface should be clean of any dust, dirt, oil or loose layers. Do not apply to wet walls.

Exterior walls:

- When applying on new surfaces (plaster, concrete, drywall, skim coat, etc.): After the substrate is completely cured (at least two weeks) apply Bonding Primer. When applying on old surfaces (old sprayed plaster, renovated or repaired walls, etc.): Peel any loose paint and perform touch-up. Then, apply Surface Strengthening Primer.

Interior walls:

- When applying on new surfaces (plaster, concrete, drywall, skim coat, etc.): After surface is completely dried (at least two weeks) apply Bonding Primer or First Coat. When applying on old surfaces (old sprayed plaster, renovated or repaired walls, etc.): Peel any loose paint and perform touch-up. Then, apply Interior Bond (Bonder All Interior).
- After preparing the surface, apply **MaxiFlax** according to the desired texture.
- For smooth texture: Thin MaxiFlax with 10% water and apply the first layer with an airless device or a fine roller in several coats, according to the required finish.
- For 'orange peel' texture: Thin MaxiFlax with 10% water and apply the first layer with an airless device or a fine roller. After the first layer has dried (about six hours), apply the second of MaxiFlax without thinning.
- For fine, medium and coarse textures: Apply MaxiFlax in two layers, using a spray gun or a roller.

Bridging and coverage rate table:

- To bridge gaps of 0.2 mm, coverage rate is: 0.35 kg/sqm in one layer.
- To bridge gaps of 0.5 mm, coverage rate is: 0.7 kg/sqm in one layer.
- To bridge gaps of 1 mm, coverage rate is: 0.7 kg/sqm in two layers (total weight: 1.4 kg/sqm).
- To bridge gaps of 2 mm, coverage rate is: 0.7 kg/sqm in three layers (total weight: 2.1 kg/sqm).

www.nadir.co.il

אזור תעשייה פרדס חנה, ת.ד. 1285, 37000 • טל. 04-6271003 • פקס. 04-6273668



MaxiFlax

Technical data

Application temperature: 5-30 degrees Celcius



Color – Nadir catalog colors



Package – 18 liter and 5 liter steel drums



Composition – flexible acrylic resin, selected aggregates, rheological materials, fungus and mold-repellent substances, and selected pigments.



Cleaned with water



Storage: dry, shady place



Application – roller or airless



Drying time between coats: 3-4 hours. Fully dried: 48 hours.



Coverage rate: See bridging table.



Shelf life: 12 months in original packing



Density – 1.60 kg/liter



Safety warnings and instructions:

- Do not apply **MaxiFlax** when rain is expected 36 hours after application.
- Do not apply to wet walls.
- Do not apply when the temperature is under five degrees or over 30.
- Do not mix this product with products not recommended by us.
- Not for internal consumption; keep out of reach of children.
- Keep storage area properly ventilated.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

www.nadir.co.il

אזור תעשייה פרדס חנה, ת.ד. 1285, 37000 • טל. 04-6271003 • פקס. 04-6273668